

### **Amendments to the Claims:**

This listing of claims will replace all prior versions, and listings, of claims in the application:

### **Listing of Claims:**

1. (Original) A lens sheet for a screen comprising one or at least two layers, adapted for use in combination with other lens sheet,  
the layer in contact with said other lens being formed of a thermoplastic resin, said thermoplastic resin having a universal hardness of 31.0 to 42.0 N/mm<sup>2</sup>.
2. (Original) The lens sheet for screen according to claim 1, wherein said thermoplastic resin has a compression modulus of elasticity of 1600 to 2500 MPa and a maximum deformation quantity of 2.0 to 2.7  $\mu\text{m}$  as measured by a creep test.
3. (Currently Amended) The lens sheet for a screen according to claim 1 ~~or 2~~, wherein said thermoplastic resin has a loss tangent at -20°C of not less than 0.04 and an elastic work ratio of not less than 70%.
4. (Currently Amended) The lens sheet for a screen according to ~~any one of claims 1 to 3~~ claim 1, wherein, when the lens sheet for a screen has a single-layer structure, said thermoplastic resin has a water absorption of not more than 0.2%.
5. (Currently Amended) The lens sheet for a screen according to ~~any one of claims 1 to 4~~ claim 1, wherein, when the lens sheet for a screen comprises two or more layers, a relationship represented by  $\alpha 1 - \alpha 2 > 0.1\%$  is satisfied wherein  $\alpha 1$  represents the water absorption of the thermoplastic resin constituting the layer in contact with said other lens, %; and  $\alpha 2$  represents the water absorption of the resin constituting the layer(s) other than the layer in contact with said other lens, %.
6. (Currently Amended) The lens sheet for a screen according to ~~any one of claims 1 to 5~~ claim 1, wherein said thermoplastic resin composition comprises a copolymer of methyl methacrylate, styrene and butadiene rubber, and the content of said methyl methacrylate and styrene is not less than 20% by weight based on said copolymer.
7. (Currently Amended) Use of a lens sheet for a screen according to ~~any one of claims 1 to 6~~ claim 1 as a lenticular lens.

8. (Original) A projection screen comprising a lenticular lens according to claim 7 and a Fresnel lens.

9. (Currently Amended) A thermoplastic resin for use in a lens sheet for a screen according to ~~any one of claims 1 to 8~~claim 1, said thermoplastic resin having a universal hardness of 31.0 to 43.0 N/mm<sup>2</sup>.

10. (Original) A thermoplastic resin according to claim 9, which has a compression modulus of elasticity of 1600 to 2500 MPa and a maximum deformation quantity of 1.95 to 2.7  $\mu\text{m}$  as measured by a creep test.

11. (Currently Amended) The thermoplastic resin according to claim 9 ~~or 10~~, wherein said thermoplastic resin has a loss tangent at -20°C of not less than 0.04 and an elastic work ratio of not less than 70%.